

ADDENDUM TO TEAL SHEETS
International Alloy Designations and Chemical Composition Limits for
Wrought Aluminum and Wrought Aluminum Alloys – February 2009

New Alloys

Updated: October 23, 2009

Alloy Designations, and Chemical Composition Limits Registered Since February 2009

Registered International Designation			Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ag	B	Bi	Ga	Li	Pb	Sn	V	Zr		OTHERS		ALUMINUM
No.	Date	By																				Each	Total	Minimum
3065	2008-12-01	USA	0.30	0.30	0.40-0.8	0.6-0.9	0.25	...	0.05	0.05	0.05	0.05	0.15	Remainder
5854	2009-02-05	Germany	0.40	0.40	0.10	0.50	2.8-3.6	0.30	...	0.20	0.15	0.0009	0.01	0.05-0.30	Ca 0.0009 Na 0.0009 Mn+Cr 0.10-0.6	0.05	0.15	Remainder
6068	2009-06-25	Switzerland	0.6-1.4	0.50	0.10	0.40-1.0	0.6-1.2	0.30	0.05	0.30	0.20	0.6-1.1	0.03	...	0.20-0.40	...	0.05	0.05	0.15	Remainder
7181	2009-08-03	Germany	0.08	0.10	1.2-1.9	0.15	1.7-2.2	0.04	...	6.7-7.9	0.06	0.08-0.18	...	0.05	0.15	Remainder

Revised Alloys

Revisions to Table of Chemical Composition Limits Since February 2009

ALLOY DESIGNATION	
1445	Deletion of 0.50 Si + Fe limit

Deactivation

Alloy Designations Deactivated Since February 2009

ALLOY DESIGNATION	DATE RECLASSIFIED	