

Errata

Table 3.1 of the Aluminum brazing handbook

Alloy	Approximate Melting Range	
	° F	°C
1350	1195-1215	646-657
1100	1190-1215	643-657
3003	1190-1210	643-654
3004	1165- <i>1210</i>	629-654
5005	<i>1170-1210</i>	632-654
5050	<i>1155-1205</i>	624-652
5052	1125-1200	607-649
5154	1100-1190	593-643
5456	1055-1180	568-638
6061	1080-1205	582-652
6063	1140- <i>1210</i>	616-654
6101	1150-1210	621-654
6151	1090-1200	588-649
6951	1140-1210	616-654
7004	1120-1195	604-646
7005	1125-1195	607-646
7072	<i>1185-1215</i>	<i>641-657</i>

Note – The entries in **bold** indicate significant corrections from the published entries in Table 3.1 of the Aluminum brazing handbook (Fourth Edition 1990 – Reaffirmed 1998). The entries in *italics* indicate relatively minor modifications (10°F or less).

Use of the Information

Any data and suggestions contained in this publication were compiled and/or developed by the Aluminum Association, Inc. In view of the variety of conditions and methods of use to which such data and suggestions may be applied, The Aluminum Association and its member companies assume no responsibility or liability for the use of information contained herein. Neither the Aluminum Association nor any of its member companies give any warranties, express or implied, with respect to this information.