

ADDENDUM TO 2018 EDITION OF YELLOW SHEETS
Tempers for Aluminum and Aluminum Alloy Products

July 24, 2023

New and Revised Registrations Since Publication of 2018 Edition of Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
2043-T85	Universal Alloy	02/07/2019	Extrusion	0.040-0.249	*Min ⁶	76.0	70.0	6	*Tentative
				0.250-0.499	*Min ⁶	78.0	73.0	7	Cross-sectional area less than or equal to 23 in ² and circle size less than or equal to 16 in.
				0.500-0.999	*Min ⁶	80.0	75.0	7	Solution heat treated and cold worked in the range 3-6% and artificially aged.
				1.000-2.500	*Min ⁶	82.0	78.0	7	<u>Stress Corrosion Resistance</u> For ST specimens taken from section thicknesses 0.75 in and greater, See footnote 4b. <u>Exfoliation Corrosion Resistance</u> See footnote 15b. Note: ASTM G85 Annex A2 Dry-Bottom MASTMAASIS Method for 2 weeks.
2050-T34	Constellium	01/25/2016 Revised 08/04/2017 Revised 02/01/2019	Plate	0.500-6.500	Min ⁹	50.0	34.0	17	Solution heat treated and cold worked 3-4.5%.

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

4.b. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: b. 35 ksi.

4.e. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: e. 45 ksi.

15. b. Material shall be capable of demonstrating exfoliation corrosion resistance. Exfoliation corrosion resistance shall be determined in accordance with ASTM G34 and material shall not exhibit exfoliation corrosion greater than that illustrated by Photo EB, Figure 2. The applicable sample plane for testing is indicated by one of the following locations: b. At the T/10 plane.

ADDENDUM TO 2018 EDITION OF YELLOW SHEETS
Tempers for Aluminum and Aluminum Alloy Products

July 24, 2023

New and Revised Registrations Since Publication of 2018 Edition of Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
2081-T84	Kaiser	11/16/2018	Plate	1.000-2.000	*Min ⁶	76.0	73.0	8	*Tentative Solution heat treated and cold worked 2-5%.
					*Min ⁹	76.0	70.0	7	
					*Min ¹⁰	72.0	62.0	2	
				2.001-3.000	*Min ⁶	74.0	71.0	6	
					*Min ⁹	75.0	68.0	6	
					*Min ¹⁰	72.0	62.0	2	
				3.001-4.000	*Min ⁶	73.0	70.0	6	
					*Min ⁹	74.0	67.0	4	
					*Min ¹⁰	71.0	62.0	2	
2050-T84	Constellium	11/21/2022	Plate	6.501-7.000	*Min ⁶	70.0	66.0	4	*Tentative Solution heat treated and cold worked approximately 3-4.5% and artificially aged <u>Stress Corrosion Resistance</u> For thicknesses 6.501 – 8.000 inches Direct C-rings and Tensile specimens machined and tested in accordance with ASTM G47 shall show no evidence of stress corrosion failure when tested in the short transverse direction at 45 ksi and exposed for 30 days. <u>Fracture Toughness</u> ¹⁴ – Min K _{IC} For thicknesses 6.501 – 7.000 inches L-T direction 22 ksi/in T-L direction 18 ksi/in S-L direction 16 ksi/in For thicknesses 7.001 – 8.000 inches L-T direction 20 ksi/in T-L direction 16 ksi/in S-L direction 15 ksi/in
					*Min ⁹	70.0	63.0	3	
					*Min ¹⁰	68.0	58.0	1.5	
				7.001-8.000	*Min ⁶	69.0	65.0	3	
					*Min ⁹	69.0	62.0	2	
					*Min ¹⁰	66.0	57.0	1.5	

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

4.b. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: b. 35 ksi.

4.e. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: e. 45 ksi.

15. b. Material shall be capable of demonstrating exfoliation corrosion resistance. Exfoliation corrosion resistance shall be determined in accordance with ASTM G34 and material shall not exhibit exfoliation corrosion greater than that illustrated by Photo EB, Figure 2. The applicable sample plane for testing is indicated by one of the following locations: b. At the T/10 plane.

ADDENDUM TO 2018 EDITION OF YELLOW SHEETS
Tempers for Aluminum and Aluminum Alloy Products

July 24, 2023

New and Revised Registrations Since Publication of 2018 Edition of Yellow Sheets										
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²	
Alloy Temper	By	Date			Basis ¹	Ult.	Yield			
2297-T87	McCook Metals	06/21/2000	Plate	1.500-2.000	Min ⁶	64.0	58.0	10	<u>Stress Corrosion Resistance</u> 30 days at 45 ksi when tested in the ST direction per ASTM G47 in the thickness range of 3.001-5.100 inches. Product outside this thickness rage will continue to exhibit capability of 30 days at 30 ksi. <u>Exfoliation Corrosion Resistance</u> See footnote 15.b. <u>Fracture Toughness</u> ¹⁴ – Min K _{IC} For thicknesses 1.500-3.000 inches L-T direction 32 ksi √in. T-L direction 27 ksi √in. S-L direction 20 ksi √in. For thicknesses 3.001-4.000 inches L-T direction 31 ksi √in. T-L direction 27 ksi √in. S-L direction 20 ksi √in. For thicknesses 4.001-5.000 inches L-T direction 30 ksi √in. T-L direction 26 ksi √in. S-L direction 18 ksi √in. For thicknesses 5.001-6.000 inches L-T direction 29 ksi √in. T-L direction 25 ksi √in. S-L direction 18 ksi √in.	
		Revised				Min ⁹	66.0	60.0		8
		06/03/2004				Min ¹⁰	65.0	57.0		2
	Constellium	Revised		01/12/2022	2.001-2.500	Min ⁶	63.0	57.0		9
						Min ⁹	64.0	58.0		7
						Min ¹⁰	64.0	56.0		2
	2.501-3.000	Min ⁶		62.0	57.0	9				
		Min ⁹		64.0	58.0	7				
		Min ¹⁰		62.0	55.0	2				
	3.001-4.000	Min ⁶		62.0	57.0	5				
		Min ⁹		62.0	57.0	4				
		Min ¹⁰		59.0	54.0	1.5				
	4.001-5.000	Min ⁶		61.0	56.0	5				
		Min ⁹		61.0	56.0	4				
		Min ¹⁰		58.0	52.0	1.5				
	5.001-6.000	Min ⁶		60.0	55.0	5				
		Min ⁹		60.0	55.0	4				
		Min ¹⁰		57.0	52.0	1.5				

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

4.b. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: b. 35 ksi.

4.e. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: e. 45 ksi.

15. b. Material shall be capable of demonstrating exfoliation corrosion resistance. Exfoliation corrosion resistance shall be determined in accordance with ASTM G34 and material shall not exhibit exfoliation corrosion greater than that illustrated by Photo EB, Figure 2. The applicable sample plane for testing is indicated by one of the following locations: b. At the T/10 plane.

ADDENDUM TO 2018 EDITION OF YELLOW SHEETS
Temper for Aluminum and Aluminum Alloy Products

July 24, 2023

New and Revised Registrations Since Publication of 2018 Edition of Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
2397-T87	Alcoa Revised Arconic	02/12/2003	Plate	3.001-4.000	Min ⁶	62.0	57.0	5	<u>Stress Corrosion Resistance</u> See footnote 4.b. <u>Exfoliation Corrosion Resistance</u> See footnote 15.b. <u>Fracture Toughness¹⁴ – Min K_{Ic}</u> For thickness 3.001-4.000 L-T direction 31 ksi Vin. T-L direction 27 ksi Vin. S-L direction 20 ksi Vin.
		Revised 08/17/2005			Min ⁹	62.0	57.0	4	
		Revised 08/02/2018			Min ¹⁰	60.0	54.0	1.5	
6061-T651	Constellium	09/09/2019	Plate	6.001-8.000	Min ⁹	42.0	36.0	9	*Tentative
				8.001-10.000	Min ⁹	41.0	34.0	8	
				10.001-12.000	Min ⁹	40.0	32.0	8	
7048-T6511	Kaiser	04/08/2020	Extrusion	0.040 – 0.125	Min ⁶	67.0	63.0	10	
7055-T76511	Alcoa Revised Arconic	01/15/2001	Extruded Rod, Bar & Profile	Up thru 0.249	Min ⁶	89.0	85.0	7	<u>Exfoliation Corrosion Resistance</u> See footnote 15. b. For thickness up thru 0.499 Inch Cross Sectional Area 12 in. ² and Circle Size 10 in. max. For thickness 0.500 – 3.000 Inch Cross Sectional Area 26.3 in. ² and Circle Size 15.3 in. max. Longitudinal Compressive Yield Strength: 87.0 ksi
		Revised 06/20/2007		0.250 – 0.499	Min ⁶	90.0	85.0	9	
		Revised 08/14/2020		0.500 – 3.000	Min ⁶	91.0	86.0	9	

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

4.b. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: b. 35 ksi.

4.e. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: e. 45 ksi.

15. b. Material shall be capable of demonstrating exfoliation corrosion resistance. Exfoliation corrosion resistance shall be determined in accordance with ASTM G34 and material shall not exhibit exfoliation corrosion greater than that illustrated by Photo EB, Figure 2. The applicable sample plane for testing is indicated by one of the following locations: b. At the T/10 plane.

ADDENDUM TO 2018 EDITION OF YELLOW SHEETS
Tempers for Aluminum and Aluminum Alloy Products

July 24, 2023

New and Revised Registrations Since Publication of 2018 Edition of Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
7160-T7351	Constellium	11/08/2018 Revised 02/06/2020	Plate	1.000-1.500	Min ⁶	74.0	67.0	13	<u>Stress Corrosion Resistance</u> See footnote 4e. <u>Fracture Toughness¹⁴</u> – Min K _{IC} or K _Q For thicknesses 1.000-2.000 inches L-T direction 40 ksi/in T-L direction 34 ksi/in For thicknesses 2.001-3.000 inches L-T direction 45 ksi/in T-L direction 33 ksi/in S-L direction 35 ksi/in For thicknesses 3.001-4.000 inches L-T direction 38 ksi/in T-L direction 30 ksi/in S-L direction 34 ksi/in For thicknesses 4.001-5.000 inches L-T direction 36 ksi/in T-L direction 27 ksi/in S-L direction 31 ksi/in For thicknesses 5.001-6.000 inches L-T direction 28 ksi/in T-L direction 25 ksi/in S-L direction 26 ksi/in
				Min ⁹	74.0	65.0	11		
				1.501-2.000	Min ⁶	73.0	67.0	13	
				Min ⁹	73.0	65.0	11		
				2.001-3.000	Min ⁶	72.0	65.0	12	
				Min ⁹	73.0	64.0	10		
				Min ¹⁰	70.0	59.0	6		
				3.001-4.000	Min ⁶	71.0	64.0	12	
				Min ⁹	72.0	63.0	9		
				Min ¹⁰	70.0	58.0	5		
				4.001-5.000	Min ⁶	70.0	64.0	11	
				Min ⁹	72.0	62.0	8		
				Min ¹⁰	69.0	58.0	4		
				5.001-6.000	Min ⁶	70.0	63.0	11	
				Min ⁹	71.0	61.0	7		
Min ¹⁰	68.0	58.0	3						

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

4.b. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: b. 35 ksi.

4.e. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: e. 45 ksi.

15. b. Material shall be capable of demonstrating exfoliation corrosion resistance. Exfoliation corrosion resistance shall be determined in accordance with ASTM G34 and material shall not exhibit exfoliation corrosion greater than that illustrated by Photo EB, Figure 2. The applicable sample plane for testing is indicated by one of the following locations: b. At the T/10 plane.

ADDENDUM TO 2018 EDITION OF YELLOW SHEETS
Tempers for Aluminum and Aluminum Alloy Products

July 24, 2023

New and Revised Registrations Since Publication of 2018 Edition of Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
7140-T7651	Alcan Revised Constellium	08/01/06 Revised 03/27/14	Plate	4.001-5.000	Min ⁶	74.0	70.0	7	<u>Stress Corrosion Resistance</u> Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to 26 ksi for 20 days. <u>Exfoliation Corrosion Resistance</u> See footnote 15.b. <u>Fracture Toughness</u> ¹⁴ – Min K _{IC} For thicknesses 4.001-5.000 inches L-T direction 27 ksi/in. T-L direction 22 ksi/in. S-L direction 22 ksi/in. For thicknesses 5.001-6.000 inches L-T direction 25 ksi/in. T-L direction 21 ksi/in. S-L direction 22 ksi/in. For thicknesses 6.001-7.000 inches L-T direction 24 ksi/in. T-L direction 20 ksi/in. S-L direction 22 ksi/in. For thicknesses 7.001-8.000 inches L-T direction 22 ksi/in. T-L direction 19 ksi/in. S-L direction 21 ksi/in. For thicknesses 8.001-9.000 inches L-T direction 20 ksi/in. T-L direction 18 ksi/in. S-L direction 20 ksi/in.
					Min ⁹	76.0	69.0	6	
					Min ¹⁰	73.0	63.0	3	
	Revised Constellium	02/27/23		5.001-6.000	Min ⁶	74.0	70.0	7	
					Min ⁹	75.0	68.0	4	
					Min ¹⁰	72.0	62.0	3	
	6.001-7.000	Min ⁶		73.0	69.0	7			
		Min ⁹		75.0	68.0	3			
		Min ¹⁰		71.0	62.0	3			
	7.001-8.000	Min ⁶	72.0	69.0	6				
		Min ⁹	74.0	67.0	3				
		Min ¹⁰	71.0	61.0	3				
	8.001-9.000	Min ⁶	72.0	68.0	5				
		Min ⁹	73.0	65.0	3				
		Min ¹⁰	69.0	60.0	3				
	9.001-10.000	Min ⁶	71.0	67.0	5				
		Min ⁹	71.0	64.0	2				
		Min ¹⁰	68.0	59.0	3				

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

4.b. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: b. 35 ksi.

4.e. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: e. 45 ksi.

15. b. Material shall be capable of demonstrating exfoliation corrosion resistance. Exfoliation corrosion resistance shall be determined in accordance with ASTM G34 and material shall not exhibit exfoliation corrosion greater than that illustrated by Photo EB, Figure 2. The applicable sample plane for testing is indicated by one of the following locations: b. At the T/10 plane.

ADDENDUM TO 2018 EDITION OF YELLOW SHEETS
Tempers for Aluminum and Aluminum Alloy Products

July 24, 2023

New and Revised Registrations Since Publication of 2018 Edition of Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
									For thicknesses 9.001-10.000 inches L-T direction 18 ksi/in. T-L direction 17 ksi/in. S-L direction 20 ksi/in.

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

4.b. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: b. 35 ksi.

4.e. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: e. 45 ksi.

15. b. Material shall be capable of demonstrating exfoliation corrosion resistance. Exfoliation corrosion resistance shall be determined in accordance with ASTM G34 and material shall not exhibit exfoliation corrosion greater than that illustrated by Photo EB, Figure 2. The applicable sample plane for testing is indicated by one of the following locations: b. At the T/10 plane.

ADDENDUM TO 2018 EDITION OF YELLOW SHEETS
Tempers for Aluminum and Aluminum Alloy Products

July 24, 2023

New and Revised Registrations Since Publication of 2018 Edition of Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
P 1	Constellium	11/02/2018	Plate	1.000-1.500	*Min ⁶	77.0	71.0	14	*Tentative <u>Stress Corrosion Resistance</u> See footnote 4b. <u>Fracture Toughness</u> ¹⁴ – Min K _{IC} or K _Q For thicknesses 1.000-1.500 inches L-T direction 34 ksi/in T-L direction 29 ksi/in For thicknesses 1.501-2.000 inches L-T direction 34 ksi/in T-L direction 29 ksi/in For thicknesses 2.001-3.000 inches L-T direction 32 ksi/in T-L direction 27 ksi/in S-L direction 28 ksi/in For thicknesses 3.001-4.000 inches L-T direction 30 ksi/in T-L direction 25 ksi/in S-L direction 27 ksi/in For thicknesses 4.001-5.000 inches L-T direction 28 ksi/in T-L direction 24 ksi/in S-L direction 26 ksi/in For thicknesses 5.001-6.000 inches L-T direction 26 ksi/in T-L direction 22 ksi/in S-L direction 25 ksi/in
					*Min ⁹	76.0	69.0	13	
				1.501-2.000	*Min ⁶	77.0	71.0	14	
					*Min ⁹	76.0	69.0	12	
					*Min ¹⁰	73.0	64.0	6	
				2.001-3.000	*Min ⁶	75.0	69.0	13	
					*Min ⁹	75.0	68.0	11	
					*Min ¹⁰	73.0	64.0	6	
				3.001-4.000	*Min ⁶	73.0	68.0	13	
					*Min ⁹	75.0	67.0	10	
					*Min ¹⁰	72.0	62.0	4	
				4.001-5.000	*Min ⁶	72.0	67.0	11	
					*Min ⁹	74.0	66.0	9	
					*Min ¹⁰	70.0	61.0	3	
				5.001-6.000	*Min ⁶	72.0	66.0	10	
					*Min ⁹	73.0	65.0	6	
					*Min ¹⁰	69.0	61.0	2	

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

4.b. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: b. 35 ksi.

4.e. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: e. 45 ksi.

15. b. Material shall be capable of demonstrating exfoliation corrosion resistance. Exfoliation corrosion resistance shall be determined in accordance with ASTM G34 and material shall not exhibit exfoliation corrosion greater than that illustrated by Photo EB, Figure 2. The applicable sample plane for testing is indicated by one of the following locations: b. At the T/10 plane.

ADDENDUM TO 2018 EDITION OF YELLOW SHEETS
Tempers for Aluminum and Aluminum Alloy Products

July 24, 2023

New and Revised Registrations Since Publication of 2018 Edition of Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
7160-T7651	Constellium	12/05/2017 Revised 12/19/2018	Plate	1.000-1.500	Min ^e	79.0	74.0	13	<u>Stress Corrosion Resistance</u> See footnote 4a. <u>Fracture Toughness</u> ⁴ – Min K _{IC} or K _{IC} For thicknesses 1.000-2.000 inches L-T direction 34 ksi/in T-L direction 29 ksi/in For thicknesses 2.001-3.000 inches L-T direction 32 ksi/in T-L direction 27 ksi/in S-L direction 29 ksi/in For thicknesses 3.001-4.000 inches L-T direction 29 ksi/in T-L direction 26 ksi/in S-L direction 28 ksi/in
					Min ^g	78.0	72.0	13	
				1.501-2.000	Min ^e	78.0	74.0	12	
					Min ^g	78.0	72.0	12	
					Min ^o	75.0	66.0	6	
				2.001-3.000	Min ^e	76.0	72.0	12	
					Min ^g	77.0	71.0	11	
					Min ^o	74.0	65.0	5	
				3.001-4.000	Min ^e	75.0	72.0	12	
					Min ^g	77.0	70.0	10	
					Min ^o	73.0	64.0	4	
				4.001-5.000	Min ^e	74.0	71.0	11	
Min ^g	76.0	69.0	9						
Min ^o	73.0	64.0	4						
7085-T711	Alcoa Revised Arconic	10/25/2011 Revised 08/02/2018	Plate	0.500-1.500	Min ^g	80.0	74.0	11	Solution heat treated, stretched 1.5 to 3%, and overaged for ballistic performance. 0.500-3.000 in. plate meets armor plate requirements of MIL-DTL-32375 (MR) Class I Type A. <u>Exfoliation Corrosion Resistance</u> See footnote 15.b.
				1.501-2.000	Min ^g	78.0	73.0	11	
				2.001-3.000	Min ^g	77.0	72.0	10	
				3.001-4.000	Min ^g	76.0	70.0	7	

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

4.b. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: b. 35 ksi.

4.e. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: e. 45 ksi.

15. b. Material shall be capable of demonstrating exfoliation corrosion resistance. Exfoliation corrosion resistance shall be determined in accordance with ASTM G34 and material shall not exhibit exfoliation corrosion greater than that illustrated by Photo EB, Figure 2. The applicable sample plane for testing is indicated by one of the following locations: b. At the T/10 plane.

ADDENDUM TO 2018 EDITION OF YELLOW SHEETS
Tempers for Aluminum and Aluminum Alloy Products

July 24, 2023

New and Revised Registrations Since Publication of 2018 Edition of Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks²
Alloy Temper	By	Date			Basis¹	Ult.	Yield		
7085-T721	Alcoa Revised Arconic	10/27/2011 Revised 08/02/2018	Plate	0.500-1.500	Min ⁹	68.0	60.0	12	Solution heat treated, stretched 1.5 to 3%, and overaged for ballistic performance. 0.500-3.000 in. plate meets armor plate requirements of MIL-DTL-32375 (MR) Class I Type B. <u>Exfoliation Corrosion Resistance</u> See footnote 15.b.
				1.501-2.000	Min ⁹	67.0	59.0	12	
				2.001-3.000	Min ⁹	67.0	58.0	11	
				3.001-4.000	Min ⁹	66.0	57.0	10	
7099-T731	Kaiser	03/13/2020	Plate	2.000-3.000	*Min ⁹	68.0	58.0	12	*Tentative Solution heat treated, stretched 1.5 to 3%, and artificially aged to meet armor plate requirements. Developed to meet armor plate requirements of MIL-DTL-32375 (Revision B Amendment 2). <u>Exfoliation Corrosion Resistance</u> See footnote 15.b.
A206-T4	Eck Industries	09/14/2020	Sand Casting	-	Min	51.0	31.0	9	Properties are from separate standard cast coupons.
A206-T7	Eck Industries	09/14/2020	Sand Casting	-	Min	50.0	35.0	2	Properties are from separate standard cast coupons.
E357-T61	Eck Industries	02/17/2017	Sand Casting	-	Min	40.0	34.0	1	Values represent properties obtained from separately cast bars and are derived from ASTM B-26, Standard Specification for Aluminum-Alloy Sand Castings.

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

4.b. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: b. 35 ksi.

4.e. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: e. 45 ksi.

15. b. Material shall be capable of demonstrating exfoliation corrosion resistance. Exfoliation corrosion resistance shall be determined in accordance with ASTM G34 and material shall not exhibit exfoliation corrosion greater than that illustrated by Photo EB, Figure 2. The applicable sample plane for testing is indicated by one of the following locations: b. At the T/10 plane.

ADDENDUM TO 2018 EDITION OF YELLOW SHEETS
Tempers for Aluminum and Aluminum Alloy Products

July 24, 2023

Tentative Removed			
Alloy Temper	Product	By	Revised Date
2397-T87	Plate	Arconic	08/02/2018
7085-T711	Plate	Arconic	08/02/2018
7085-T721	Plate	Arconic	08/02/2018
7160-T7351	Plate	Constellium	02/06/2020
7160-T7651	Plate	Constellium	12/19/2018
2050-T34	Plate	Constellium	02/01/2019

Deactivated Tempers		
Alloy /Temper	Product	Date Deactivated
Alclad 2024-O ²	Sheet & Plate	08/11/2018
Alclad 2024-T351 ²	Plate	08/11/2018
Alclad 2024-T42 ²	Sheet & Plate	08/11/2018
1 ½% Alclad 2024-O ²	Sheet & Plate	08/11/2018
1 ½% Alclad 2024-T351 ²	Plate	08/11/2018
1 ½% Alclad 2024-T42 ²	Sheet & Plate	08/11/2018

++ Deactivation is limited to specific gauge range(s) for the product indicated

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

4.b. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: b. 35 ksi.

4.e. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: e. 45 ksi.

15. b. Material shall be capable of demonstrating exfoliation corrosion resistance. Exfoliation corrosion resistance shall be determined in accordance with ASTM G34 and material shall not exhibit exfoliation corrosion greater than that illustrated by Photo EB, Figure 2. The applicable sample plane for testing is indicated by one of the following locations: b. At the T/10 plane.