

ADDENDUM TO PINK SHEETS
Designations and Chemical Composition Limits for Aluminum Alloys
in the Form of Castings and Ingot

January 7, 2025

Alloy Designation and Chemical Composition Limits Registered Since Publication of 2018 Edition of the Pink Sheets																						
Designation			Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ag	Be	Pb	Sn	Zr		FNs	OTHERS ¹²		Al	
AA No.	Date REGISTERED	PRODUCTS ⁵																	Each	Total ³	Minimum	
G356.0	2024-08-02	Casting	6.5-8.0	0.35 Max	0.25 Max	0.20 Max	0.15-0.6	0.10-0.30	-	0.20 Max	0.20 Max	-	-	-	-	-	-	-	-	0.05	0.15	Rem.
G356.1	2024-08-02	Ingot	6.5-8.0	0.25 Max	0.25 Max	0.20 Max	0.20-0.6	0.10-0.30	-	0.20 Max	0.20 Max	-	-	-	-	-	-	-	-	0.05	0.15	Rem.
G356.2	2024-08-02	Ingot	6.5-8.0	0.25 Max	0.10 Max	0.15 Max	0.20-0.55	0.10-0.15	-	0.10 Max	0.20 Max	-	-	-	-	-	-	-	-	0.05	0.15	Rem.
527.0	2021-03-05	Casting	-	-	-	-	9.5-10.0	-	-	-	-	-	-	-	-	-	Ce 7.2-8.8	-	0.10	0.50	Rem.	
527.1	2021-03-05	Ingot	-	-	-	-	9.7-10.0	-	-	-	-	-	-	-	-	-	Ce 7.4-8.8	-	0.08	0.40	Rem.	
727.0	2021-03-05	Casting	-	0.25-0.50	-	-	2.3-2.7	-	0.6-0.7	5.7-6.0	-	-	-	-	-	-	Ce 3.5-4.0	-	0.10	0.50	Rem.	
727.1	2021-03-05	Ingot	-	0.25-0.45	-	-	2.4-2.7	-	0.6-0.7	5.7-6.0	-	-	-	-	-	-	Ce 3.6-4.0	-	0.08	0.40	Rem.	

Unless specified below, for referenced footnotes refer to the Pink Sheets as applicable.