

**ADDENDUM TO 2018 EDITION OF YELLOW SHEETS**  
**Tempers for Aluminum and Aluminum Alloy Products**

June 26, 2020

New and Revised Registrations Since Publication of 2018 Edition of Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks <sup>2</sup>
Alloy Temper	By	Date			Basis <sup>1</sup>	Ult.	Yield		
2043-T85	Universal Alloy	02/07/2019	Extrusion	0.040-0.249	*Min <sup>6</sup>	76.0	70.0	6	*Tentative
				0.250-0.499	*Min <sup>6</sup>	78.0	73.0	7	Cross-sectional area less than or equal to 23 in <sup>2</sup> and circle size less than or equal to 16 in.
				0.500-0.999	*Min <sup>6</sup>	80.0	75.0	7	
				1.000-2.500	*Min <sup>6</sup>	82.0	78.0	7	Solution heat treated and cold worked in the range 3-6% and artificially aged.  <u>Stress Corrosion Resistance</u> For ST specimens taken from section thicknesses 0.75 in and greater, See footnote 4b.  <u>Exfoliation Corrosion Resistance</u> See footnote 15b. Note: ASTM G85 Annex A2 Dry-Bottom MASTMAASIS Method for 2 weeks.
2050-T34	Constellium	01/25/2016 Revised 08/04/2017 Revised 02/01/2019	Plate	0.500-6.500	Min <sup>9</sup>	50.0	34.0	17	Solution heat treated and cold worked 3-4.5%.
2081-T84	Kaiser	11/16/2018	Plate	1.000-2.000	*Min <sup>6</sup>	76.0	73.0	8	*Tentative  Solution heat treated and cold worked 2-5%.
					*Min <sup>9</sup>	76.0	70.0	7	
				2.001-3.000	*Min <sup>6</sup>	74.0	71.0	6	
					*Min <sup>9</sup>	75.0	68.0	6	
				*Min <sup>10</sup>	72.0	62.0	2		

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

4.b. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: b. 35 ksi.

4.e. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: e. 45 ksi.

15. b. Material shall be capable of demonstrating exfoliation corrosion resistance. Exfoliation corrosion resistance shall be determined in accordance with ASTM G34 and material shall not exhibit exfoliation corrosion greater than that illustrated by Photo EB, Figure 2. The applicable sample plane for testing is indicated by one of the following locations: b. At the T/10 plane.

**ADDENDUM TO 2018 EDITION OF YELLOW SHEETS**  
**Tempers for Aluminum and Aluminum Alloy Products**

June 26, 2020

New and Revised Registrations Since Publication of 2018 Edition of Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks <sup>2</sup>
Alloy Temper	By	Date			Basis <sup>1</sup>	Ult.	Yield		
				3.001-4.000	*Min <sup>6</sup>	73.0	70.0	6	
					*Min <sup>9</sup>	74.0	67.0	4	
					*Min <sup>10</sup>	71.0	62.0	2	
2397-T87	Alcoa	02/12/2003	Plate	3.001-4.000	Min <sup>6</sup>	62.0	57.0	5	<u>Stress Corrosion Resistance</u> See footnote 4.b.  <u>Exfoliation Corrosion Resistance</u> See footnote 15.b.  <u>Fracture Toughness<sup>14</sup> – Min K<sub>Ic</sub></u> For thickness 3.001-4.000 L-T direction 31 ksi √in. T-L direction 27 ksi √in. S-L direction 20 ksi √in.
		Revised 08/17/2005			Min <sup>9</sup>	62.0	57.0	4	
	Revised Arconic	Revised 08/02/2018			Min <sup>10</sup>	60.0	54.0	1.5	
6060-T651	Constellium	09/09/2019	Plate	6.001-8.000	Min <sup>9</sup>	42.0	36.0	9	*Tentative
				8.001-10.000	Min <sup>9</sup>	41.0	34.0	8	
				10.001-12.000	Min <sup>9</sup>	40.0	32.0	8	
7048-T6511	Kaiser	04/08/2020	Extrusion	0.040 – 0.125	Min <sup>6</sup>	67.0	63.0	10	
7160-T7351	Constellium	11/08/2018	Plate	1.000-1.500	Min <sup>6</sup>	74.0	67.0	13	<u>Stress Corrosion Resistance</u> See footnote 4e.
				Revised 02/06/2020	1.501-2.000	Min <sup>6</sup>	74.0	65.0	
					Min <sup>6</sup>	73.0	67.0	13	
					Min <sup>9</sup>	73.0	65.0	11	

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

4.b. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: b. 35 ksi.

4.e. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: e. 45 ksi.

15. b. Material shall be capable of demonstrating exfoliation corrosion resistance. Exfoliation corrosion resistance shall be determined in accordance with ASTM G34 and material shall not exhibit exfoliation corrosion greater than that illustrated by Photo EB, Figure 2. The applicable sample plane for testing is indicated by one of the following locations: b. At the T/10 plane.

**ADDENDUM TO 2018 EDITION OF YELLOW SHEETS**  
**Tempers for Aluminum and Aluminum Alloy Products**

June 26, 2020

New and Revised Registrations Since Publication of 2018 Edition of Yellow Sheets										
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks <sup>2</sup>	
Alloy Temper	By	Date			Basis <sup>1</sup>	Ult.	Yield			
				2.001-3.000	Min <sup>6</sup> Min <sup>9</sup> Min <sup>10</sup>	72.0 73.0 70.0	65.0 64.0 59.0	12 10 6	Fracture Toughness <sup>14</sup> – Min K <sub>IC</sub> or K <sub>ICQ</sub> For thicknesses 1.000-2.000 inches L-T direction 40 ksi/in T-L direction 34 ksi/in	
				3.001-4.000	Min <sup>6</sup> Min <sup>9</sup> Min <sup>10</sup>	71.0 72.0 70.0	64.0 63.0 58.0	12 9 5	For thicknesses 2.001-3.000 inches L-T direction 45 ksi/in T-L direction 33 ksi/in	
				4.001-5.000	Min <sup>6</sup> Min <sup>9</sup> Min <sup>10</sup>	70.0 72.0 69.0	64.0 62.0 58.0	11 8 4	S-L direction 35 ksi/in For thicknesses 3.001-4.000 inches L-T direction 38 ksi/in	
				5.001-6.000	Min <sup>6</sup> Min <sup>9</sup> Min <sup>10</sup>	70.0 71.0 68.0	63.0 61.0 58.0	11 7 3	T-L direction 30 ksi/in S-L direction 34 ksi/in For thicknesses 4.001-5.000 inches L-T direction 36 ksi/in T-L direction 27 ksi/in S-L direction 31 ksi/in	
									For thicknesses 5.001-6.000 inches L-T direction 28 ksi/in T-L direction 25 ksi/in S-L direction 26 ksi/in	
P 1	7160-T7451	Constellium	11/02/2018	Plate	1.000-1.500	*Min <sup>6</sup> *Min <sup>9</sup>	77.0 76.0	71.0 69.0	14 13	*Tentative <u>Stress Corrosion Resistance</u> See footnote 4b.
					1.501-2.000	*Min <sup>6</sup> *Min <sup>9</sup> *Min <sup>10</sup>	77.0 76.0 73.0	71.0 69.0 64.0	14 12 6	

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

4.b. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: b. 35 ksi.

4.e. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: e. 45 ksi.

15. b. Material shall be capable of demonstrating exfoliation corrosion resistance. Exfoliation corrosion resistance shall be determined in accordance with ASTM G34 and material shall not exhibit exfoliation corrosion greater than that illustrated by Photo EB, Figure 2. The applicable sample plane for testing is indicated by one of the following locations: b. At the T/10 plane.

**ADDENDUM TO 2018 EDITION OF YELLOW SHEETS**  
**Tempers for Aluminum and Aluminum Alloy Products**

June 26, 2020

New and Revised Registrations Since Publication of 2018 Edition of Yellow Sheets										
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks <sup>2</sup>	
Alloy Temper	By	Date			Basis <sup>1</sup>	Ult.	Yield			
				2.001-3.000	*Min <sup>6</sup> *Min <sup>9</sup> *Min <sup>10</sup>	75.0 75.0 73.0	69.0 68.0 64.0	13 11 6	<u>Fracture Toughness</u> <sup>14</sup> – Min K <sub>IC</sub> or K <sub>IC</sub> For thicknesses 1.000-1.500 inches L-T direction 34 ksi/in T-L direction 29 ksi/in  For thicknesses 1.501-2.000 inches L-T direction 34 ksi/in T-L direction 29 ksi/in  For thicknesses 2.001-3.000 inches L-T direction 32 ksi/in T-L direction 27 ksi/in S-L direction 28 ksi/in  For thicknesses 3.001-4.000 inches L-T direction 30 ksi/in T-L direction 25 ksi/in S-L direction 27 ksi/in  For thicknesses 4.001-5.000 inches L-T direction 28 ksi/in T-L direction 24 ksi/in S-L direction 26 ksi/in  For thicknesses 5.001-6.000 inches L-T direction 26 ksi/in T-L direction 22 ksi/in S-L direction 25 ksi/in	
				3.001-4.000	*Min <sup>6</sup> *Min <sup>9</sup> *Min <sup>10</sup>	73.0 75.0 72.0	68.0 67.0 62.0	13 10 4		
				4.001-5.000	*Min <sup>6</sup> *Min <sup>9</sup> *Min <sup>10</sup>	72.0 74.0 70.0	67.0 66.0 61.0	11 9 3		
				5.001-6.000	*Min <sup>6</sup> *Min <sup>9</sup> *Min <sup>10</sup>	72.0 73.0 69.0	66.0 65.0 61.0	10 6 2		
7160-T7651	Constellium	12/05/2017 Revised 12/19/2018	Plate	1.000-1.500	Min <sup>6</sup> Min <sup>9</sup>	79.0 78.0	74.0 72.0	13 13		<u>Stress Corrosion Resistance</u> See footnote 4a.

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

4.b. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: b. 35 ksi.

4.e. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: e. 45 ksi.

15. b. Material shall be capable of demonstrating exfoliation corrosion resistance. Exfoliation corrosion resistance shall be determined in accordance with ASTM G34 and material shall not exhibit exfoliation corrosion greater than that illustrated by Photo EB, Figure 2. The applicable sample plane for testing is indicated by one of the following locations: b. At the T/10 plane.

**ADDENDUM TO 2018 EDITION OF YELLOW SHEETS**  
**Tempers for Aluminum and Aluminum Alloy Products**

June 26, 2020

New and Revised Registrations Since Publication of 2018 Edition of Yellow Sheets										
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks <sup>2</sup>	
Alloy Temper	By	Date			Basis <sup>1</sup>	Ult.	Yield			
				1.501-2.000	Min <sup>6</sup>	78.0	74.0	12	<u>Fracture Toughness<sup>14</sup></u> – Min K <sub>IC</sub> or K <sub>IC</sub> For thicknesses 1.000-2.000 inches L-T direction 34 ksi√in T-L direction 29 ksi√in  For thicknesses 2.001-3.000 inches L-T direction 32 ksi√in T-L direction 27 ksi√in S-L direction 29 ksi√in  For thicknesses 3.001-4.000 inches L-T direction 29 ksi√in T-L direction 26 ksi√in S-L direction 28 ksi√in	
				2.001-3.000	Min <sup>9</sup>	78.0	72.0	12		
					Min <sup>10</sup>	75.0	66.0	6		
					Min <sup>6</sup>	76.0	72.0	12		
				3.001-4.000	Min <sup>9</sup>	77.0	71.0	11		
					Min <sup>10</sup>	74.0	65.0	5		
					Min <sup>6</sup>	75.0	72.0	12		
				4.001-5.000	Min <sup>9</sup>	77.0	70.0	10		
					Min <sup>10</sup>	73.0	64.0	4		
					Min <sup>6</sup>	74.0	71.0	11		
7085-T711	Alcoa Revised Arconic	10/25/2011 Revised 08/02/2018	Plate	0.500-1.500	Min <sup>9</sup>	80.0	74.0	11		Solution heat treated, stretched 1.5 to 3%, and overaged for ballistic performance.  0.500-3.000 in. plate meets armor plate requirements of MIL-DTL-32375 (MR) Class I Type A.  <u>Exfoliation Corrosion Resistance</u> See footnote 15.b.
				1.501-2.000	Min <sup>9</sup>	78.0	73.0	11		
				2.001-3.000	Min <sup>9</sup>	77.0	72.0	10		
				3.001-4.000	Min <sup>9</sup>	76.0	70.0	7		
7085-T721	Alcoa Revised Arconic	10/27/2011 Revised 08/02/2018	Plate	0.500-1.500	Min <sup>9</sup>	68.0	60.0	12	Solution heat treated, stretched 1.5 to 3%, and overaged for ballistic performance.  0.500-3.000 in. plate meets armor plate requirements of MIL-DTL-32375 (MR) Class I Type B.	
				1.501-2.000	Min <sup>9</sup>	67.0	59.0	12		
				2.001-3.000	Min <sup>9</sup>	67.0	58.0	11		
				3.001-4.000	Min <sup>9</sup>	66.0	57.0	10		

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

4.b. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: b. 35 ksi.

4.e. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: e. 45 ksi.

15. b. Material shall be capable of demonstrating exfoliation corrosion resistance. Exfoliation corrosion resistance shall be determined in accordance with ASTM G34 and material shall not exhibit exfoliation corrosion greater than that illustrated by Photo EB, Figure 2. The applicable sample plane for testing is indicated by one of the following locations: b. At the T/10 plane.

**ADDENDUM TO 2018 EDITION OF YELLOW SHEETS**  
**Tempers for Aluminum and Aluminum Alloy Products**

**June 26, 2020**

New and Revised Registrations Since Publication of 2018 Edition of Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks <sup>2</sup>
Alloy Temper	By	Date			Basis <sup>1</sup>	Ult.	Yield		
									<u>Exfoliation Corrosion Resistance</u> See footnote 15.b.
7099-T731	Kaiser	03/13/2020	Plate	2.000-3.000	*Min <sup>9</sup>	68.0	58.0	12	*Tentative  Solution heat treated, stretched 1.5 to 3%, and artificially aged to meet armor plate requirements. Developed to meet armor plate requirements of MIL-DTL-32375 (Revision B Amendment 2).  <u>Exfoliation Corrosion Resistance</u> See footnote 15.b.
E357-T61	Eck Industries	02/17/2017	Sand Casting	-	Min	40.0	34.0	1	Values represent properties obtained from separately cast bars and are derived from ASTM B-26, Standard Specification for Aluminum-Alloy Sand Castings.

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

4.b. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: b. 35 ksi.

4.e. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: e. 45 ksi.

15. b. Material shall be capable of demonstrating exfoliation corrosion resistance. Exfoliation corrosion resistance shall be determined in accordance with ASTM G34 and material shall not exhibit exfoliation corrosion greater than that illustrated by Photo EB, Figure 2. The applicable sample plane for testing is indicated by one of the following locations: b. At the T/10 plane.

**ADDENDUM TO 2018 EDITION OF YELLOW SHEETS**  
**Tempers for Aluminum and Aluminum Alloy Products**

June 26, 2020

Tentative Removed			
Alloy Temper	Product	By	Revised Date
2397-T87	Plate	Arconic	08/02/2018
7085-T711	Plate	Arconic	08/02/2018
7085-T721	Plate	Arconic	08/02/2018
7160-T7351	Plate	Constellium	02/06/2020
7160-T7651	Plate	Constellium	12/19/2018
2050-T34	Plate	Constellium	02/01/2019

Deactivated Tempers		
Alloy /Temper	Product	Date Deactivated
Alclad 2024-O <sup>2</sup>	Sheet & Plate	08/11/2018
Alclad 2024-T351 <sup>2</sup>	Plate	08/11/2018
Alclad 2024-T42 <sup>2</sup>	Sheet & Plate	08/11/2018
1 ½% Alclad 2024-O <sup>2</sup>	Sheet & Plate	08/11/2018
1 ½% Alclad 2024-T351 <sup>2</sup>	Plate	08/11/2018
1 ½% Alclad 2024-T42 <sup>2</sup>	Sheet & Plate	08/11/2018

++ Deactivation is limited to specific gauge range(s) for the product indicated

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

4.b. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: b. 35 ksi.

4.e. Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when stressed to: e. 45 ksi.

15. b. Material shall be capable of demonstrating exfoliation corrosion resistance. Exfoliation corrosion resistance shall be determined in accordance with ASTM G34 and material shall not exhibit exfoliation corrosion greater than that illustrated by Photo EB, Figure 2. The applicable sample plane for testing is indicated by one of the following locations: b. At the T/10 plane.