

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Temper For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

New and Revised Registrations Since Publication of 2011 Edition of the Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
2111-T8	Kaiser	01/18/2018	Rod & Bar	0.500-3.500	*Min ⁶	52.0	38.0	10	* Tentative Cold finished Rod & Bar used primarily in, but not limited to, machining applications.
2013-T4511	Sumitomo	08/01/2012	Drawn Tube	0.120-0.400	*Min ⁶	40.0	21.0	20	* Tentative
2013-T6511	Sumitomo	12/15/2011	Drawn Tube	0.120-0.400	*Min ⁶	60.0	56.0	7	* Tentative
2624-T351	Alcoa	06/22/2011 Revised 10/22/2013	Plate	0.500-1.000	Min ⁶ Min ⁹	63.0 65.0	48.0 44.0	16 15	Fracture Toughness ¹⁴ – Min K _{IC} or K _{IQ} For thicknesses 0.750-1.500 inches L-T direction 42 ksi vin T-L direction 41 ksi vin
				1.001-1.500	Min ⁶ Min ⁹	62.0 64.0	47.0 44.0	16 15	
2624-T39	Alcoa	01/28/2011	Plate	0.750-1.500	Min ⁶ Min ⁹	68.0 71.0	62.0 58.0	11 9	Cold rolled ~10% and stretched ~1% after solution heat treating. Fracture Toughness ¹⁴ – K _{IC} or K _{IQ} For thicknesses 0.750-1.500 inches L-T direction 39 ksi vin. T-L direction 33 ksi vin.
2824-T3511	Universal Alloy	06/25/2014	Extrusion	0.250-0.499	*Min ⁶ *Min ⁹	71.0 68.0	54.0 48.0	12 -	*Tentative Cross-sectional area less than or equal to 25 in. ²
				0.500-0.749	*Min ⁶ *Min ⁹	73.0 68.0	55.0 47.0	11 8	
				0.750-0.999	*Min ⁶ *Min ⁹	73.0 67.0	55.0 47.0	11 8	
				1.000-1.499	*Min ⁶ *Min ⁹	74.0 66.0	56.0 47.0	11 8	
				1.500-1.999	*Min ⁶ *Min ⁹	74.0 65.0	56.0 46.0	11 8	
				2.000-2.500	*Min ⁶ *Min ⁹	74.0 64.0	56.0 46.0	10 8	

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Tempers For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

New and Revised Registrations Since Publication of 2011 Edition of the Yellow Sheets														
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²					
Alloy Temper	By	Date			Basis ¹	Ult.	Yield							
Alclad 2029-T8	Alcoa	05/12/2015	Sheet & Plate	0.063-0.164	*Min ⁶	61.0	55.0	8	*Tentative					
					*Min ⁹	61.0	54.0	9						
				0.165-0.249	*Min ⁶	61.0	55.0	10						
					*Min ⁹	61.0	54.0	10						
		0.250-0.499		*Min ⁶	61.0	56.0	11							
				*Min ⁹	61.0	54.0	10							
		0.500-0.600		*Min ⁶	63.0	58.0	13							
				*Min ⁹	64.0	56.0	11							
2139-T84	Alcan Global ATI	03/23/2011	Plate	1.000-1.500	*Min ⁶	65.0	62.0	11	* Tentative Material is cold worked in the range of 3-6% after solution heat treatment. <u>Stress Corrosion Resistance</u> For thicknesses 1.000 – 5.000 inches. C-rings and tensile specimens machined and tested in accordance with ASTM G47 shall show no evidence of stress corrosion failure when tested in the short transverse direction at 40 ksi and exposed for 30 days. <u>Fracture Toughness</u> ¹⁴ – *Min K _{IC} For thicknesses 1.000-3.750 inches L-T direction 35 ksi vin T-L direction 32 ksi vin S-L direction 27 ksi vin (from 2.000 inch) For thicknesses 3.751 – 5.000 inches L-T direction 32 ksi Vin T-L direction 30 ksi Vin S-L direction 27 ksi Vin					
					*Min ⁹	67.0	61.0	8						
					*Min ¹⁰	63.0	55.0	5						
				1.501-3.750	*Min ⁶	66.0	62.0	9						
					*Min ⁹	68.0	61.0	7						
					*Min ¹⁰	62.0	55.0	4						
				3.751-5.000	*Min ⁶	65.0	59.0	8						
					*Min ⁹	67.0	59.0	6						
					*Min ¹⁰	61.0	53.0	4						
				2050-T34	Constellium	01/25/2016	Plate	0.500-1.999		*Min ⁹	52.0	36.0	17	*Tentative
						Revised 08/04/2017		2.000-6.500		*Min ⁹	52.0	34.0	17	Solution heat treated and cold worked 3-4.5%.

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Temps For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

New and Revised Registrations Since Publication of 2011 Edition of the Yellow Sheets										
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²	
Alloy Temper	By	Date			Basis ¹	Ult.	Yield			
2050-T84	Alcan	03/23/2007	Plate	0.500 – 1.500	Min ⁶	73.0	69.0	9	<u>Stress Corrosion Resistance</u> For thickness 0.750 – 6.500 inches Direct C-rings and Tensile specimens machined and tested in accordance with ASTM G47 shall show no evidence of stress corrosion failure when tested in the short transverse direction at 45 ksi and exposed for 30 days. <u>Fracture Toughness</u> ¹⁴ – Min K _{IC} For thicknesses 0.500 – 1.500 inches L-T direction 33 ksi √in. T-L direction 29 ksi √in. S-L direction 25 ksi √in. For thicknesses 1.501 – 2.000 inches L-T direction 31 ksi √in. T-L direction 27 ksi √in. S-L direction 23 ksi √in. For thicknesses 2.001 – 3.000 inches L-T direction 28 ksi √in. T-L direction 25 ksi √in. S-L direction 23 ksi √in. For thicknesses 3.001 – 4.000 inches L-T direction 26 ksi √in. T-L direction 23 ksi √in. S-L direction 21 ksi √in. For thicknesses 4.001 – 5.000 inches L-T direction 25 ksi √in. T-L direction 21 ksi √in. S-L direction 21 ksi √in. For thicknesses 5.001 – 6.000 inches L-T direction 22 ksi √in. T-L direction 20 ksi √in. S-L direction 18 ksi √in.	
		Revised			Min ⁹	74.0	67.0	7		
	Constellium	03/09/2012			1.501 – 2.000	Min ⁶	72.0	67.0		9
						Min ⁹	73.0	65.0		7
	Min ¹⁰	71.0		61.0	2					
	2.001 – 3.000	Min ⁶		72.0	67.0	8				
		Min ⁹		72.0	65.0	6				
		Min ¹⁰		71.0	61.0	2				
	3.001 – 4.000	Min ⁶		71.0	67.0	7				
		Min ⁹		72.0	65.0	4				
		Min ¹⁰		70.0	60.0	1.5				
	4.001 – 5.000	Min ⁶		71.0	66.0	6				
		Min ⁹		71.0	64.0	3				
		Min ¹⁰		69.0	59.0	1.5				
	5.001-6.500	Min ⁶		71.0	66.0	5				
		Min ⁹		71.0	64.0	3				
		Min ¹⁰		69.0	59.0	1.5				

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Temps For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

New and Revised Registrations Since Publication of 2011 Edition of the Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
									For thicknesses 6.001 – 6.500 inches L-T direction 22 ksi Vin. T-L direction 19 ksi Vin. S-L direction 16 ksi Vin.
2050-T852	Aubert & Duval	01/21/2014 Revised 10/01/2015	Die Forging	0.250 – 1.500	Min ⁶	75.0	69.0	9	<u>Fracture Toughness</u> ¹⁴ – K _{IC} or K _{ICQ} For thicknesses 0.250-1.500 inches L-T direction 32 ksi Vin T-L direction 29 ksi Vin For thicknesses 1.501-2.000 inches L-T direction 32 ksi Vin T-L direction 29 ksi Vin For thicknesses 2.001-3.000 inches L-T direction 29 ksi Vin T-L direction 26 ksi Vin S-L direction 20 ksi Vin For thicknesses 3.001-4.000 inches L-T direction 26 ksi Vin T-L direction 23 ksi Vin S-L direction 20 ksi Vin For thicknesses 4.001-5.000 inches L-T direction 25 ksi Vin T-L direction 21 ksi Vin S-L direction 19 ksi Vin For thicknesses 5.001-6.000 inches L-T direction 23 ksi Vin T-L direction 20 ksi Vin S-L direction 19 ksi Vin For thicknesses 6.001-7.000 inches L-T direction 22 ksi Vin T-L direction 19 ksi Vin S-L direction 18 ksi Vin
					Min ⁹	76.0	70.0	8	
				1.501 – 2.000	Min ⁶	75.0	69.0	9	
					Min ⁹	76.0	70.0	8	
					Min ¹⁰	75.0	64.0	4	
				2.001 – 3.000	Min ⁶	74.0	68.0	8	
					Min ⁹	74.0	68.0	6	
					Min ¹⁰	73.0	64.0	3	
				3.001 – 4.000	Min ⁶	74.0	68.0	7	
					Min ⁹	73.0	67.0	6	
					Min ¹⁰	73.0	63.0	3	
				4.001 – 5.000	Min ⁶	74.0	67.0	6	
	Min ⁹	73.0	66.0	6					
	Min ¹⁰	72.0	62.0	2					
5.001 – 6.000	Min ⁶	73.0	67.0	6					
	Min ⁹	72.0	65.0	6					
	Min ¹⁰	71.0	61.0	2					
6.001 – 7.000	Min ⁶	73.0	66.0	5					
	Min ⁹	71.0	64.0	5					
	Min ¹⁰	71.0	61.0	2					
7.001 – 8.000	Min ⁶	72.0	66.0	5					
	Min ⁹	71.0	63.0	5					
	Min ¹⁰	70.0	60.0	2					
8.001 – 9.000	Min ⁶	72.0	65.0	5					
	Min ⁹	70.0	63.0	5					
	Min ¹⁰	70.0	60.0	2					

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Tempers For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

New and Revised Registrations Since Publication of 2011 Edition of the Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
				9.001 – 10.000	Min ⁶ Min ⁹ Min ¹⁰	71.0 69.0 69.0	64.0 62.0 59.0	4 4 1.5	For thicknesses 7.001-8.000 inches L-T direction 21 ksi Vin T-L direction 18 ksi Vin S-L direction 17 ksi Vin For thicknesses 8.001-9.000 inches L-T direction 21 ksi Vin T-L direction 18 ksi Vin S-L direction 17 ksi Vin For thicknesses 9.001-10.000 inches L-T direction 20 ksi Vin T-L direction 18 ksi Vin S-L direction 16 ksi Vin
2055-T84	Alcoa	01/14/2014	Extrusion	0.040-0.125	*Min ⁶	82.0	78.0	5	*Tentative
				0.126-0.249	*Min ⁶ *Min ⁹	83.0 84.0	79.0 78.0	6 5	Solution heat treated and cold worked in the range 2-5% and artificially aged.
				0.250-0.499	*Min ⁶ *Min ⁹	85.0 84.0	80.0 78.0	7 5	Cross Sectional Area less than or equal to 18.5 in. ² and Circle Size less than or equal to 14.5 in.
				0.500-0.749	*Min ⁶ *Min ⁹	87.0 84.0	82.0 78.0	8 5	Fracture Toughness ¹⁴ – Min. K _{IC} or K _Q For thicknesses 0.750-1.500 inches L-T direction 22 ksi Vin T-L direction 19 ksi Vin
				0.750-1.249	*Min ⁶ *Min ⁹	88.0 84.0	84.0 78.0	8 5	
				1.250-1.500	*Min ⁶ *Min ⁹	90.0 84.0	86.0 78.0	8 5	
2060-T86	Alcoa	06/03/2013	Plate	0.750-1.500	*Min ⁶ *Min ⁹	73.0 73.0	68.0 63.0	9 6	*Tentative Solution heat treated, cold worked approximately 6% and artificially aged. Fracture Toughness ¹⁴ – Min K _{IC} or K _Q For thicknesses 0.750-1.500 inches L-T direction 38 ksi Vin. T-L direction 33 ksi Vin.

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Temper For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

New and Revised Registrations Since Publication of 2011 Edition of the Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
2065-T84	Constellium	04/16/2014	Extrusion	0.040-0.249 0.250-0.499	*Min ⁶ *Min ⁶	87.0 87.0	83.0 84.0	6 6	*Tentative Solution heat treated, cold worked approximately 3-4% and artificially aged.
2195-T8	Constellium	03/09/2012 Revised 01/20/2015	Sheet & Plate	0.125-0.499	Min ⁶ Min ⁹	82.0 80.0	78.0 76.0	6 6	
2195-T841	Constellium	06/24/2011	Plate	0.500-2.250	*Min ⁹	71.0	63.0	9	*Tentative Developed to meet armor plate requirements of Mil-STD-32341. Material is solution heat treated, cold worked in the range 3-5%, and underaged.
2395-T84	Universal Alloy	02/10/2016	Extrusion	0.040-0.125 0.126-0.249 0.250-0.499 0.500-1.500	*Min ⁶ *Min ⁹ *Min ⁶ *Min ⁹ *Min ⁶ *Min ⁹ *Min ⁶ *Min ⁹	84.0 85.0 85.0 85.0 85.0 85.0 90.0 85.0	78.0 78.0 78.0 78.0 79.0 78.0 83.0 78.0	6 5 6 5 6 5 7 5	*Tentative Cross-sectional area less than or equal to 23 in ² and circle size less than or equal to 16 in. Solution heat treated and cold worked in the range 2-5% and artificially aged.
2196-T8511	Alcan Revised Constellium	10/04/2007 Revised 03/29/2012	Extrusion	0.063-0.125 0.129-0.249 0.250-1.000	*Min ⁶ *Min ⁶ *Min ⁶	76.0 76.0 78.0	69.0 71.0 71.0	6 7 5	* Tentative
2196-T8511	Constellium	10/27/2016	Extrusion	0.040-0.062	*Min ⁶	75.0	69.0	6	* Tentative
2099-T81	Alcoa	08/01/2011	Extrusion	0.375-1.300	Min ⁶ Min ⁹	73.0 63.0	59.0 51.0	7 7	Stretched approximately 1-3 % and underaged. <u>Stress Corrosion Resistance</u> Material shall be capable of passing the stress corrosion cracking test described in ASTM G47 when tested in the LT direction at a stress of 38.4 ksi for 30 days.

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Tempers For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

New and Revised Registrations Since Publication of 2011 Edition of the Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
									<u>Exfoliation Corrosion Resistance</u> Specimens shall not exhibit exfoliation corrosion at a T/2 plane greater than that illustrated by Photo 2 (EB) from Figure 2 of ASTM G34 when specimens are exposed for 2 weeks according to the procedures in ASTM G85 Annex A2, using the dry-bottom MASTMAASIS Test Method. <u>Fracture Toughness¹⁴</u> – Min K _{IC} or K _Q For thicknesses 0.500-1.300 inch L-T direction 45 ksi vln
2199-T86	Alcoa	06/16/2011	Plate	0.750-1.250	*Min ⁶ *Min ⁹	64.0 66.0	58.0 58.0	9 8	*Tentative Solution heat treated, cold worked approximately 6% and artificially aged. <u>Exfoliation Corrosion Resistance</u> Specimens shall not exhibit exfoliation corrosion at a T/10 plane greater than that illustrated by Photo 2 (EA) from Figure 2 of ASTM G34 when specimens are exposed for 2 weeks according to the procedures in ASTM B85 Annex A2, using the dry-bottom MASTMAASIS Test Method. <u>Fracture Toughness¹⁴</u> – Min K _{IC} or K _Q For thicknesses 0.750-1.250 inches L-T direction 48 ksi vln L-T direction 43 ksi vln
3003-H22	Alcoa	04/12/2011	Sheet	0.045-0.063 0.064-0.249	Min ⁶ Min ⁶	17.0 17.0	12.0 12.0	5 7	Used for tread plate applications.
5454-H114	Alcoa	11/24/2012	Sheet	0.115-0.200	Min ⁶ Max ⁶	31.0 41.0	14.0 -	10 -	Used for tread plate applications.

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Temper For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

New and Revised Registrations Since Publication of 2011 Edition of the Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
5456-H151	Alcoa	03/22/2012	Plate	0.250-0.499	*Min ⁶ *Max ⁶	54.0 62.0	47.0 -	6 -	*Tentative Developed to meet armor plate requirements of MIL-DTL-46027K.
				0.500-2.000	*Min ⁶ *Max ⁶	50.0 61.0	45.0 -	6 -	
				2.001-3.000	*Min ⁶ *Max ⁶	50.0 60.0	44.0 -	8 -	
5083-H116	Alcan	08/18/05	Sheet & Plate	0.118-0.249	Min ⁹ Max ⁹	44.0 55.0	31.0 -	10 -	<u>Exfoliation Corrosion Resistance</u> This material shall be capable of exhibiting no evidence of exfoliation corrosion and a pitting rating of PB or better, when subjected to the test described in ASTM Test Method G 66 (ASSET). <u>Intergranular Corrosion Resistance</u> This material shall be capable of exhibiting resistance to intergranular corrosion as required by ASTM B928 when subjected to the test described in ASTM Test Method ASTM G 67 (NAMLT).
	Alcoa	Revised 12/09/14		0.250-0.499	Min ⁹ Max ⁹	44.0 55.0	31.0 -	10 -	
5083-H128	Alcoa	11/15/2012	Sheet & Plate	0.157-0.315	*Min ^{6,9} *Max ^{6,9}	44.0 56.0	31.0 -	10 -	*Tentative <u>Exfoliation Corrosion Resistance</u> After a post-production thermal treatment of 212°F (100°C) for 1 week, this material shall be capable of exhibiting no evidence of exfoliation corrosion and a pitting rating of PB or better, when subjected to the test described in ASTM Test Method G 66 (ASSET). <u>Intergranular Corrosion Resistance</u> After a post-production thermal treatment of 212°F (100°C) for 1 week, this material shall be capable of exhibiting mass-loss no greater than 100 mg/in. ² [15 mg/cm ²] when tested in accordance with ASTM Test Method G67 (NAMLT).
		Revised		0.316-0.499	*Min ^{6,9} *Max ^{6,9}	44.0 56.0	31.0 -	10 -	
		10/07/2013		0.500-1.500	*Min ^{6,9} *Max ^{6,9}	44.0 56.0	31.0 -	12 -	
				1.501-3.000	*Min ^{6,9} *Max ^{6,9}	41.0 56.0	29.0 -	12 -	

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Temper For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

New and Revised Registrations Since Publication of 2011 Edition of the Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
5383-H321	Constellium	02/10/2012	Sheet & Plate	0.118-0.500	Max ⁶	58.0	-	-	<u>Exfoliation Corrosion Resistance</u> This material shall be capable of exhibiting no evidence of exfoliation corrosion and a pitting rating of PB or better, when subjected to the test described in ASTM Test Method G 66 (ASSET). <u>Intergranular Corrosion Resistance</u> This material shall be capable of exhibiting resistance to intergranular corrosion as required by ASTM B 928 when subjected to the test described in ASTM Test Method G 67 (NAMLT).
				0.501-2.000	Max ⁶	58.0	-	-	
6105-T6	Werner	01/23/2012	Extrusion	Up thru 0.500	Min ⁶	38.0	35.0	8	The registered properties for this material are calculated in accordance with the procedure described under 3.c.1 of page ii of the Yellow Sheets.
6013-T6, & -T6511	Alcoa	03/11/2012	Extrusion, Rod and Seamless Tube	0.200-0.499	Min ⁶	49.0	46.0	8	
				0.500-0.749	Min ⁶	49.0	46.0	8	
				0.750-2.000	Min ⁶	49.0	45.0	8	
6013-T62	Alcoa	08/17/2011	Sheet	0.020-0.125	Min ⁹	52.0	46.0	8	
6026-T6	Eural GNUTTI S.p.A.	09/25/2015	Bar, Rod and Wire	0.200-3.000	Min ⁶	54.0	44.0	6	Cold Finished.
6026-T6, & -T6510 & -T6511	Eural GNUTTI S.p.A.	09/25/2015	Extruded Bar, Rod and Wire	1.300-5.500	Min ⁶	54.0	44.0	6	
				5.501-8.000	Min ⁶	49.0	36.0	6	
				8.001-10.000	Min ⁶	44.0	29.0	6	

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Temper For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

New and Revised Registrations Since Publication of 2011 Edition of the Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
6026-T6 &-T6510 &-T6511	Eural GNUTTI S.p.A.	09/25/2015	Extruded Profiles	0.200 – 1.500	Min ⁶	49.0	38.0	6	
6026-T6 & -T6510 & -T6511	Eural GNUTTI S.p.A.	09/25/2015	Extruded Tube	0.400 – 1.300	Min ⁶	49.0	38.0	6	
6026-T8	Eural GNUTTI S.p.A.	09/25/2015	Bar, Rod and Wire	0.200-3.000	Min ⁶	50.0	46.0	3	Cold Finished.
6026-T9	Eural GNUTTI S.p.A.	09/25/2015	Bar, Rod and Wire	0.200-3.000	Min ⁶	52.0	48.0	3	Cold Finished.
6063-T65	Rio Tinto Alcan	02/25/2011	Extrusion	Up thru 0.182	Min ⁶	36.0	33.0	8	6063-T65 signifies higher mechanical properties than 6063-T6. The registered properties for the material are calculated in accordance with the procedure described under 3.c.1. on page ii of this document.
6064-T6, & -T6511	Kaiser	12/21/2007 Revised 12/15/2011	Extruded Rod, Bar, and Profiles	0.180-3.250	Min ⁶	42.0	38.0	10	The registered properties for this material are calculated in accordance with the procedure described under 3.c.1 on page ii of the Yellow Sheets.
6082-T5, & -T5511	Alcoa Revised SAPA	06/11/2005 Revised 12/05/2013	Extrusion	0.080-0.500	Min ⁶	39.0	33.0	8	
7010-T7451	Constellium	07/07/2015	Plate	Up to 2.000 2.001-2.500 2.501-4.000	Min ⁶ Min ⁹ Min ⁶ Min ⁹ Min ¹⁰ Min ⁶ Min ⁹ Min ¹⁰	71.0 72.0 71.0 72.0 67.0 70.0 71.0 66.0	62.0 62.0 62.0 62.0 57.0 61.0 61.0 56.0	9 6 9 6 2.5 9 6 2	Solution heat-treated, stress relieved by stretching to produce a nominal permanent set of 2% but not less than 1-1/2% nor more than 3%, and precipitation heat treated to the T7451 temper. <u>Stress Corrosion Resistance</u> Specimens from plate, 0.750 inch and over in nominal thickness, shall show no evidence

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Tempers For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

New and Revised Registrations Since Publication of 2011 Edition of the Yellow Sheets										
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²	
Alloy Temper	By	Date			Basis ¹	Ult.	Yield			
				4.001-5.000	Min ⁶ Min ⁹ Min ¹⁰	68.0 69.0 65.0	59.0 59.0 54.0	9 5 2	of stress-corrosion cracking when tested in accordance with ASTM G47 and stressed in the short-transverse direction to 50% of the specified minimum long-transverse yield strength for plate 3 inches and under in nominal thickness and to 35.0 ksi for plate over 3 inches in nominal thickness. <u>Exfoliation Corrosion Resistance</u> Plate shall achieve an exfoliation rating of EA or better, as illustrated in ASTM G34 at the T/10 plane. <u>Fracture Toughness¹⁴ – Min K_{IC}</u> For thicknesses 2.000 to 5.500 inches, incl L-T direction 24 ksi √in T-L direction 22 ksi √in For thicknesses over 2.000 to 5.500 inches, incl S-L direction 20 ksi √in	
				5.001-6.000	Min ⁶ Min ⁹ Min ¹⁰	66.0 67.0 63.0	57.0 57.0 53.0	8 5 2		
7136-T73511	Universal Alloys	02/10/2016	Extrusion	0.040-0.249	*Min ⁶ *Min ⁹	80.0 79.0	73.0 71.0	7 4		*Tentative Cross-sectional area less than or equal to 56 in ² and circle size less than or equal to 20 in. <u>Stress Corrosion Resistance</u> For products with thickness 0.75 inch and higher when tested in ST orientation see footnote 4.e. <u>Exfoliation Corrosion Resistance</u> See footnote 15.b.
				0.250-0.499	*Min ⁶ *Min ⁹	80.0 78.0	73.0 71.0	7 4		
				0.500-0.999	*Min ⁶ *Min ⁹	80.0 77.0	73.0 69.0	7 4		
				1.000-1.499	*Min ⁶ *Min ⁹	80.0 76.0	73.0 68.0	7 4		
				1.500-1.999	*Min ⁶ *Min ⁹ *Min ¹⁰	80.0 75.0 74.0	73.0 67.0 65.0	7 4 3		
				2.000-2.999	*Min ⁶ *Min ⁹ *Min ¹⁰	80.0 74.0 74.0	73.0 66.0 65.0	7 4 3		

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Temper For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

New and Revised Registrations Since Publication of 2011 Edition of the Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
				3.000-3.999	*Min ⁶	80.0	73.0	7	
					*Min ⁹	74.0	66.0	4	
					*Min ¹⁰	74.0	65.0	3	
				4.000-4.500	*Min ⁶	80.0	73.0	7	
					*Min ⁹	74.0	66.0	4	
					*Min ¹⁰	74.0	65.0	3	
7136-T74511	Universal Alloy	02/11/2016	Extrusion	0.040-0.249	*Min ⁶	85.0	80.0	7	*Tentative
					*Min ⁹	82.0	76.0	4	Cross-sectional area less than or equal to 56 in ² and circle size less than or equal to 24 in.
				0.250-0.499	*Min ⁶	85.0	80.0	7	
					*Min ⁹	82.0	75.0	4	<u>Stress Corrosion Resistance</u>
				0.500-0.999	*Min ⁶	85.0	80.0	7	For products with thickness 0.75 inch and higher when tested in ST orientation see footnote 4.b.
					*Min ⁹	81.0	75.0	4	
				1.000-1.499	*Min ⁶	85.0	80.0	7	
					*Min ⁹	81.0	74.0	4	<u>Exfoliation Corrosion Resistance</u>
				1.500-1.999	*Min ⁶	85.0	80.0	7	See footnote 15.b.
					*Min ⁹	80.0	74.0	4	
					*Min ¹⁰	77.0	70.0	3	
				2.000-2.999	*Min ⁶	85.0	80.0	7	
					*Min ⁹	79.0	72.0	4	
					*Min ¹⁰	77.0	70.0	3	
				3.000-3.999	*Min ⁶	85.0	80.0	7	
					*Min ⁹	77.0	71.0	4	
					*Min ¹⁰	77.0	70.0	3	
				4.000-4.500	*Min ⁶	85.0	80.0	7	
					*Min ⁹	77.0	70.0	4	
					*Min ¹⁰	77.0	70.0	3	
7037-T7452	Otto-Fuchs	07/04/2011	Hand Forging	2.500-4.000	Min ⁶	71.0	64.0	10	<u>Stress Corrosion Resistance</u>
					Min ⁹	72.0	64.0	10	See footnote 4.b.
					Min ¹⁰	72.0	60.0	6	

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Temper For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

New and Revised Registrations Since Publication of 2011 Edition of the Yellow Sheets										
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²	
Alloy Temper	By	Date			Basis ¹	Ult.	Yield			
				4.001-6.000	Min ⁶ Min ⁹ Min ¹⁰	71.0 71.0 71.0	64.0 64.0 58.0	10 6 6	<u>Fracture Toughness</u> ¹⁴ – Min K _{IC} or K _Q For thicknesses 2.500-4.000 inches L-T direction 30 ksi √in T-L direction 29 ksi √in S-L direction 21 ksi √in For thicknesses 4.001-6.000 inches L-T direction 30 ksi √in T-L direction 29 ksi √in S-L direction 21 ksi √in For thicknesses 6.001-8.000 inches L-T direction 30 ksi √in T-L direction 21 ksi √in S-L direction 21 ksi √in For thicknesses 8.001-11.000 inches L-T direction 30 ksi √in T-L direction 19 ksi √in S-L direction 21 ksi √in	
				6.001-8.000	Min ⁶ Min ⁹ Min ¹⁰	70.0 70.0 69.0	63.0 62.0 57.0	10 4 6		
				8.001-11.000	Min ⁶ Min ⁹ Min ¹⁰	67.0 67.0 66.0	59.0 58.0 54.0	8 4 6		
7155-T76	Alcoa	08/07/2015	Drawn Tube	0.045-0.125	*Min ⁶	85.0	82.0	7		*Tentative Elongation values shown are for Full-section specimens.
7255-T7751	Alcoa	03/11/2011 Revised 05/13/2013	Plate	0.750-1.500	Min ⁶ Min ⁹	91.0 91.0	88.0 86.0	9 7		<u>Exfoliation Corrosion Resistance</u> See footnote 15.b. <u>Fracture Toughness</u> ¹⁴ – Min K _{IC} For thicknesses 0.750-1.500 inches L-T direction 22 Ksi √in T-L direction 21 Ksi √in Longitudinal Compressive Yield Strength for 0.750-1.500 inch : 88 ksi minimum.

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Temper For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

New and Revised Registrations Since Publication of 2011 Edition of the Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
7056-T721	Constellium	09/17/2015	Plate	1.000-3.000	*Min ⁹	64.0	56.0	11	*Tentative <u>Exfoliation Corrosion Resistance</u> See footnote 15.b. Solution heat treated, stretched 1.5 to 3%, and overaged. Developed to meet blast armor plate requirements of MIL-DTL-32375 (MR).
7056-T761	Constellium	09/17/2015	Plate	1.000-3.000	*Min ⁹	80.0	77.0	7	*Tentative <u>Stress Corrosion Cracking Resistance</u> See footnote 4.a. Solution heat treated, stretched 1.5 to 3%, and overaged. Developed to meet ballistic armor plate requirements of MIL-DTL-32375 (MR).
7160-T7651	Constellium	12/05/2017	Plate	1.000-1.500	*Min ⁶ *Min ⁹	79.0 78.0	74.0 72.0	13 13	*Tentative <u>Stress Corrosion Resistance</u> See footnote 4.a. Fracture Toughness ¹⁴ – Min K _{IC} or K _Q For thicknesses 1.000-1.500 inches L-T direction 36 ksi √in T-L direction 29 ksi √in
				1.501-2.000	*Min ⁶ *Min ⁹ *Min ¹⁰	78.0 78.0 75.0	74.0 72.0 66.0	12 12 6	
				2.001-3.000	*Min ⁶ *Min ⁹ *Min ¹⁰	76.0 77.0 74.0	72.0 71.0 65.0	12 11 5	For thicknesses 1.501-2.000 inches L-T direction 34 ksi √in T-L direction 29 ksi √in
				3.001-4.000	*Min ⁶ *Min ⁹ *Min ¹⁰	75.0 77.0 73.0	72.0 70.0 64.0	12 10 4	
				4.001-5.000	*Min ⁶ *Min ⁹ *Min ¹⁰	74.0 76.0 73.0	71.0 69.0 64.0	11 9 4	For thicknesses 2.001-3.000 inches L-T direction 32 ksi √in T-L direction 27 ksi √in S-L direction 29 ksi √in

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Tempers For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

New and Revised Registrations Since Publication of 2011 Edition of the Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
				5.001-6.000	*Min ⁶ *Min ⁹ *Min ¹⁰	74.0 75.0 72.0	70.0 68.0 63.0	10 8 4	<p>For thicknesses 3.001-4.000 inches L-T direction 29 ksi Vin T-L direction 26 ksi Vin S-L direction 28 ksi Vin</p> <p>For thicknesses 4.001-5.000 inches L-T direction 25 ksi Vin T-L direction 24 ksi Vin S-L direction 26 ksi Vin</p> <p>For thicknesses 5.001-6.000 inches L-T direction 22 ksi Vin T-L direction 23 ksi Vin S-L direction 24 ksi Vin</p>
7065-T7451	Alcoa	03/12/2014	Plate	1.000-1.500	*Min ⁶ *Min ⁹	77.0 77.0	71.0 70.0	11 10	*Tentative
				1.501 – 2.000	*Min ⁶ *Min ⁹ *Min ¹⁰	76.0 77.0 75.0	70.0 69.0 64.0	11 9 6	<p><u>Stress Corrosion Resistance</u> See footnote 4.b.</p> <p><u>Fracture Toughness¹⁴ – Min K_{IC} or K_{IC}</u></p>
				2.001-3.000	*Min ⁶ *Min ⁹ *Min ¹⁰	76.0 76.0 74.0	70.0 68.0 64.0	10 8 5	<p>For thicknesses 1.000-1.500 inches L-T direction 39 ksiVin T-L direction 30 ksiVin</p>
				3.001-4.000	*Min ⁶ *Min ⁹ *Min ¹⁰	75.0 75.0 73.0	69.0 68.0 63.0	9 7 4	<p>For thicknesses 1.501-2.000 inches L-T direction 36 ksiVin T-L direction 29 ksiVin</p>
				4.001-5.000	*Min ⁶ *Min ⁹ *Min ¹⁰	75.0 75.0 73.0	69.0 68.0 63.0	9 6 3	<p>For thicknesses 2.001-3.000 inches L-T direction 32 ksiVin T-L direction 27 ksiVin S-L direction 25 ksiVin</p>
				5.001-6.000	*Min ⁶ *Min ⁹ *Min ¹⁰	74.0 75.0 73.0	69.0 67.0 63.0	8 5 3	<p>For thicknesses 3.001-4.000 inches L-T direction 28 ksiVin T-L direction 24 ksiVin S-L direction 23 ksiVin</p>

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Tempers For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

New and Revised Registrations Since Publication of 2011 Edition of the Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
									For thicknesses 4.001-5.000 inches L-T direction 26 ksi \bar{V} in T-L direction 22 ksi \bar{V} in S-L direction 21 ksi \bar{V} in For thicknesses 5.001-6.000 inches L-T direction 25 ksi \bar{V} in T-L direction 21 ksi \bar{V} in S-L direction 21 ksi \bar{V} in
7065-T7651	Alcoa	03/12/2014	Plate	1.000-1.500	*Min ⁶ *Min ⁹	80.0 80.0	76.0 73.0	10 9	*Tentative <u>Stress Corrosion Resistance</u> See footnote 4.a. <u>Fracture Toughness¹⁴ – Min K_{IC} or K_Q</u>
				1.501-2.000	*Min ⁶ *Min ⁹ *Min ¹⁰	79.0 80.0 78.0	75.0 73.0 68.0	10 9 6	For thicknesses 1.000-1.500 inches L-T direction 35 ksi \bar{V} in T-L direction 27 ksi \bar{V} in
				2.001-3.000	*Min ⁶ *Min ⁹ *Min ¹⁰	78.0 79.0 77.0	74.0 72.0 68.0	9 8 4	For thicknesses 1.501-2.000 inches L-T direction 32 ksi \bar{V} in T-L direction 27 ksi \bar{V} in
				3.001-4.000	*Min ⁶ *Min ⁹ *Min ¹⁰	78.0 78.0 77.0	74.0 71.0 67.0	9 6 3	For thicknesses 2.001-3.000 inches L-T direction 29 ksi \bar{V} in T-L direction 25 ksi \bar{V} in S-L direction 23 ksi \bar{V} in
				4.001-5.000	*Min ⁶ *Min ⁹ *Min ¹⁰	77.0 78.0 76.0	74.0 71.0 67.0	8 5 3	For thicknesses 3.001-4.000 inches L-T direction 25 ksi \bar{V} in T-L direction 23 ksi \bar{V} in S-L direction 22 ksi \bar{V} in
				5.001-6.000	*Min ⁶ *Min ⁹ *Min ¹⁰	76.0 77.0 75.0	74.0 71.0 67.0	7 5 3	

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Tempers For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

New and Revised Registrations Since Publication of 2011 Edition of the Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
									For thicknesses 4.001-5.000 inches L-T direction 24 ksi \bar{v} in T-L direction 21 ksi \bar{v} in S-L direction 21 ksi \bar{v} in For thicknesses 5.001-6.000 inches L-T direction 23 ksi \bar{v} in T-L direction 20 ksi \bar{v} in S-L direction 20 ksi \bar{v} in
7085-T711	Alcoa	10/25/2011	Plate	0.500-1.500	*Min ⁹	80.0	74.0	11	*Tentative
				1.501-2.000	*Min ⁹	78.0	73.0	11	Solution heat treated, stretched 1.5 to 3%, and overaged for ballistic performance.
				2.001-3.000	*Min ⁹	77.0	72.0	10	Developed to meet armor plate requirements of MIL-DTL-32375 (MR).
				3.001-4.000	*Min ⁹	76.0	70.0	7	<u>Exfoliation Corrosion Resistance</u> See footnote 15.b.
7085-T721	Alcoa	10/27/2011	Plate	0.500-1.500	*Min ⁹	68.0	60.0	12	*Tentative
				1.501-2.000	*Min ⁹	67.0	59.0	12	Solution heat treated, stretched 1.5 to 3%, and overaged for blast performance.
				2.001-3.000	*Min ⁹	67.0	58.0	11	Developed to meet armor plate requirements of MIL-DTL-32375 (MR).
				3.001-4.000	*Min ⁹	66.0	57.0	10	<u>Exfoliation Corrosion Resistance</u> See footnote 15.b.
7085-T7451	Alcoa	02/03/2009 Revised 07/09/2012	Plate	3.000-4.000	Min ⁶ Min ⁹ Min ¹⁰	73.0 73.0 72.0	68.0 66.0 61.0	11 8 4	<u>Stress Corrosion Resistance</u> See footnotes 4.b. <u>Fracture Toughness</u> ¹⁴ — Min K _{IC} or K _Q
				4.001-5.000	Min ⁶ Min ⁹ Min ¹⁰	73.0 73.0 71.0	68.0 66.0 61.0	10 7 4	For thickness 3.000-4.000 inches L-T direction 36 ksi \bar{v} in. T-L direction 27 ksi \bar{v} in. S-L direction 27 ksi \bar{v} in.

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Tempers For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

New and Revised Registrations Since Publication of 2011 Edition of the Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
				5.001-6.000	Min ⁶ Min ⁹ Min ¹⁰	72.0 73.0 70.0	68.0 65.0 61.0	9 6 4	For thickness 4.001-5.000 inches L-T direction 32 ksi vin. T-L direction 25 ksi vin.
				6.001-7.000	Min ⁶ Min ⁹ Min ¹⁰	72.0 72.0 69.0	67.0 64.0 60.0	8 5 4	For thickness 5.001-6.000 inches L-T direction 29 ksi vin. T-L direction 23 ksi vin. S-L direction 24 ksi vin.
									For thickness 6.001-7.000 inches L-T direction 29 ksi vin. T-L direction 22 ksi vin. S-L direction 23 ksi vin.
7097-T7651	Kaiser	12/30/2015	Plate	3.000-4.000	*Min ⁶ *Min ⁹ *Min ¹⁰	74.0 77.0 75.0	71.0 71.0 66.0	12 7 4	*Tentative <u>Exfoliation Corrosion Resistance</u> See Footnote 15.b.
				4.001-5.000	*Min ⁶ *Min ⁹ *Min ¹⁰	74.0 76.0 74.0	71.0 70.0 65.0	11 6 3	
				5.001-6.000	*Min ⁶ *Min ⁹ *Min ¹⁰	74.0 76.0 73.0	71.0 69.0 65.0	9 4 3	
				6.001-7.000	*Min ⁶ *Min ⁹ *Min ¹⁰	74.0 75.0 72.0	70.0 68.0 64.0	8 3 3	
				7.001-8.000	*Min ⁶ *Min ⁹ *Min ¹⁰	73.0 74.0 71.0	69.0 67.0 63.0	6 3 3	

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Temper For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

New and Revised Registrations Since Publication of 2011 Edition of the Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
7099-T7451	Kaiser	01/22/2013 Revised 04/07/2015	Plate	1.000-1.500	Min ⁶	77.0	71.0	11	<u>Stress Corrosion Cracking Resistance</u> See Footnote 4.b.
					Min ⁹	77.0	70.0	10	
					Min ¹⁰	76.0	65.0	6	
				1.501-2.000	Min ⁶	76.0	71.0	11	
					Min ⁹	77.0	69.0	9	
					Min ¹⁰	76.0	65.0	6	
				2.001-3.000	Min ⁶	76.0	70.0	10	
					Min ⁹	76.0	68.0	8	
					Min ¹⁰	74.0	64.0	5	
				3.001-4.000	Min ⁶	75.0	69.0	9	
					Min ⁹	76.0	68.0	7	
					Min ¹⁰	74.0	63.0	4	
				4.001-5.000	Min ⁶	75.0	69.0	9	
					Min ⁹	75.0	68.0	6	
					Min ¹⁰	74.0	63.0	3	
				5.001-6.000	Min ⁶	74.0	68.0	8	
					Min ⁹	75.0	67.0	5	
					Min ¹⁰	73.0	62.0	3	
7099-T7651	Kaiser	01/22/2013 Revised 04/07/2015	Plate	1.000-1.500	Min ⁶	79.0	75.0	10	<u>Stress Corrosion Cracking Resistance</u> See Footnote 4.a.
					Min ⁹	80.0	74.0	9	
					Min ¹⁰	77.0	68.0	5	
				1.501-2.000	Min ⁶	79.0	75.0	10	
					Min ⁹	80.0	74.0	9	
					Min ¹⁰	77.0	68.0	5	
				2.001-3.000	Min ⁶	78.0	73.0	9	
					Min ⁹	79.0	72.0	8	
					Min ¹⁰	77.0	67.0	4	
				3.001-4.000	Min ⁶	77.0	72.0	9	
					Min ⁹	79.0	71.0	6	
					Min ¹⁰	77.0	67.0	3	
				4.001-5.000	Min ⁶	76.0	71.0	8	
					Min ⁹	78.0	70.0	5	
					Min ¹⁰	76.0	66.0	3	

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Tempers For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

New and Revised Registrations Since Publication of 2011 Edition of the Yellow Sheets									
Registered			Product	Thickness in.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date			Basis ¹	Ult.	Yield		
				5.001-6.000	Min ⁶	76.0	70.0	7	
					Min ⁹	77.0	70.0	5	
					Min ¹⁰	74.0	65.0	3	

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Tempers For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

Tentative Removed Publication of 2011 Edition of the Yellow Sheets			
Alloy Temper	Product	By	Revised Date
6064-T6 & -T6511	Extruded Rod, Bar and Profiles	Kaiser	12/15/2011
7140-T7651	Plate	Constellium	03/27/2014
7150-T7751	Plate	Alcoa	07/27/2011
7055-O	Sheet	Alcoa	01/19/2011
7099-T7451	Plate	Kaiser	04/07/2015
7099-T7651	Plate	Kaiser	04/07/2015
2050-T852	Die Forging	Aubert & Duval	10/02/2015

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Tempers For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

Reactivated Tempers Publication of 2011 Edition of the Yellow Sheets											
Registered			Reactivated		Product	Thickness In.	Tensile Strength, ksi			Elongation Percent in 2 in. or 4D	Remarks ²
Alloy Temper	By	Date	By	Date			Basis ¹	Ult.	Yield		
2090-T86	Alcoa	08/11/88 Revised 07/30/90	Alcoa	07/18/2012	Extrusion	Up thru 0.124	Min ⁶	78.0	71.0	4	
						0.125-0.249	Min ⁶	78.0	71.0	5	
						0.250-0.499	Min ⁶	80.0	73.0	5	
							Min ⁹	76.0	68.0	-	

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Tempers For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

Deactivated Tempers Publication of 2011 Edition of the Yellow Sheets		
Alloy /Temper	Product	Date Deactivated
2090-T86	Extrusion	03/07/2011
6111-T6	Sheet	12/21/2011
7055-T762	Sheet	05/04/2011
Alclad 2014-O ⁺⁺	Plate	06/28/2012
Alclad 2014-T42 ⁺⁺	Plate	06/28/2012
Alclad 2014-T451 ⁺⁺	Plate	06/28/2012
Alclad 2014-T62 ⁺⁺	Plate	06/28/2012
Alclad 2014-T651 ⁺⁺	Plate	06/28/2012
Alclad 2219-O ⁺⁺	Plate	06/28/2012
Alclad 2219-T62 ⁺⁺	Plate	06/28/2012
Alclad 6061-O ⁺⁺	Plate	06/28/2012
Alclad 6061-T42 ⁺⁺	Plate	06/28/2012
Alclad 6061-T451 ⁺⁺	Plate	06/28/2012
Alclad 6061-T62 ⁺⁺	Plate	06/28/2012
Alclad 6061-T651 ⁺⁺	Plate	06/28/2012
Alclad 7075-O ⁺⁺	Plate	06/28/2012
Alclad 7075-T62 ⁺⁺	Plate	06/28/2012
Alclad 7075-T651 ⁺⁺	Plate	06/28/2012
Alclad 7075-T7351 ⁺⁺	Plate	06/28/2012
Alclad 7075-T7651 ⁺⁺	Plate	06/28/2012
2 ½% Alclad 7075-O ⁺⁺	Plate	06/28/2012
2 ½% Alclad 7075-T62 ⁺⁺	Plate	06/28/2012
2 ½% Alclad 7075-T651 ⁺⁺	Plate	06/28/2012
2 ½% Alclad 7075-T7351 ⁺⁺	Plate	06/28/2012
2 ½% Alclad 7075-T7651 ⁺⁺	Plate	06/28/2012
Alclad One Side 7075-O ⁺⁺	Plate	06/28/2012

⁺⁺ Deactivation is limited to specific gauge range(s) for the product indicated

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.

ADDENDUM TO 2011 EDITION OF YELLOW SHEETS
Tempers For Aluminum And Aluminum Alloy Products

Rev. April 11, 2018

Deactivated Tempers Since Publication of 2011 Edition of the Yellow Sheets		
Alloy /Temper	Product	Date Deactivated
Alclad One Side 7075-T62 ⁺⁺	Plate	06/28/2012
Alclad One Side 7075-T651 ⁺⁺	Plate	06/28/2012
2 ½% Alclad One Side 7075-O ⁺⁺	Plate	06/28/2012
2 ½% Alclad One Side 7075-T62 ⁺⁺	Plate	06/28/2012
2 ½% Alclad One Side 7075-T651 ⁺⁺	Plate	06/28/2012
7250-T7451	Plate	05/29/2014
6082-T5 & -T5511 ⁺⁺	Extrusion	07/09/2014
2024-T72	Sheet	11/25/2014
Alclad 2024-T72	Sheet	11/25/2014
1½% Alclad 2024-T72	Sheet	11/25/2014
Alclad One Side 2024-T72	Sheet	11/25/2014
1½% Alclad One Side 2024-T72	Sheet	11/25/2014
7033-T6	Die Forging	12/02/2015

⁺⁺ Deactivation is limited to specific gauge range(s) for the product indicated

Unless specified below, for all referenced footnotes refer to the Yellow and/or Tan Sheets as applicable.